

NR Pro 35

Technology

Nanotechnology
UV Stable Dye

Color Tone

Graphite

Construction

2-Ply Weatherable

Thickness

1.5 Mil

Color Stable

Yes

Catalogue Number

R058P5A



Optical & Solar Properties

| | |
|------------------------------------|------|
| Ultra Violet Block | >99% |
| Visible Light Transmitted | 37% |
| Visible Light Reflected (exterior) | 8% |
| Glare Reduction | 58% |
| SIRR | 46% |
| IRER | 34% |
| Shading Coefficient | 0.68 |
| Total Solar Energy Reflected | 7% |
| Total Solar Energy Transmitted | 45% |
| Total Solar Energy Absorbed | 48% |
| Total Solar Energy Rejected | 41% |

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards