



# DR OptiTune 15i

## Optical & Solar Properties

	Single Pane	Double Pane
Visible Light Transmitted	13%	13%
Visible Light Reflected (interior)	25%	24%
Visible Light Reflected (exterior)	56%	56%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	51%	46%
Total Solar Energy Transmitted	12%	11%
Total Solar Energy Absorbed	37%	43%
Emissivity (Room Side)	0.76	0.76
Glare Reduction	85%	85%
Selective InfraRed Reduction (SIRR)	88%	88%
InfraRed Energy Rejection (IRER)	77%	77%
Shading Coefficient	0.26	0.37
Solar Heat Gain Coeff. (G-Value)	0.22	0.32
U-Value Winter (IP)	1.00	0.47
U-Value Winter (SI)	5.68	2.67
Luminous Efficacy	0.50	0.34
Total Solar Energy Rejected	78%	68%

R070R1W - Water Activated Adhesive



Powered by  
NanoTechnology

