



R Silver 20X Poly

Optical & Solar Properties

	Single Pane
Visible Light Transmitted	16%
Visible Light Reflected (interior)	63%
Visible Light Reflected (exterior)	64%
Ultra Violet Block	99%
Total Solar Energy Reflected	65%
Total Solar Energy Transmitted	12%
Total Solar Energy Absorbed	23%
Emissivity (Room Side)	0.84
Glare Reduction	82%
Selective InfraRed Reduction (SIRR)	90%
InfraRed Energy Rejection (IRER)	84%
Shading Coefficient	0.22
Solar Heat Gain Coeff. (G-Value)	0.19
U-Value Winter (IP)	1.04
U-Value Winter (SI)	5.91
Luminous Efficacy	0.75
Total Solar Energy Rejected	81%

R0705XP - Pressure Sensitive Adhesive

