

PRODUCT DATA SHEET

Avery Dennison[®] Paint Protection Film SPF Satin

Issued: 05/2026

Introduction

AD Supreme Protection Film SPF-Satin is an engineered thermoplastic polyurethane film in transparent clear satin finish, designed to protect a vehicle's finish against stone chips, road debris, insect stains, small to medium scratches, chemical stains and weathering, without degrading the original paint. SPF-Satin has a "self-healing" top coat, which helps small scratches in the film disappear when film is exposed to heat. The top coat of SPF-Satin has been specially designed to enhance its stain resistance, making the film easier to clean and maintain, and reduce potential discolouration or yellowing from stains or interaction with chemicals.

Conversion

SPF-Satin is designed for vehicle paint and painted surface protection purposes and is easy to size by manual cutting during application or digital cutting plotters. It is also possible to apply SPF-Satin on top of pre-existing and applied Avery Dennison Supreme Wrapping Film™. SPF-Satin should be applied using the wet application method. For more information please refer to TB. 6.0 Application Instructions for Avery Dennison™ SPF Series.



Face Film

165 micron, top-coated thermoplastic polyurethane, satin finish (protected PET sheet is not included)



Adhesive

Permanent, acrylic based



Backing

PET liner



Durability

Zone 1 vertical 10 years



Shelf Life

1 year Stored at 22°C 50-55% RH

Recommendations

- › Protection of the highly sensitive external surfaces of the vehicle, such as bumper, side mirrors, hood & wheel arches.
- › Protection of painted internal metal surfaces, such as luggage racks or chairs in buses or trains.
- › Protection of painted metal surfaces in high traffic areas, such as reception desks, door impact areas, wall panels and more.

Features

- › SPF-Satin top coat enhances stain resistance, eases cleaning and minimizes yellowing. Many stains such as motor oil, sharpie marker and mustard can be cleaned just with a dried microfiber cloth.
- › Heat activated self-healing top coat provides good scratch resistance & recovery.
- › Protection of painted surfaces from stone chips, road debris, insect stains and weathering.
- › Exceptional visual properties - enhancing the look of the vehicle; optical clarity & satin finish.
- › Up to 10 years protection- maintaining the quality of vehicle finish.
- › Premium grade, conformable thermoplastic polyurethane (TPU) film.

Physical Characteristics

	Test method ¹	Results	
Product			
Caliper, facefilm including topcoat (micron)	ISO 534	165	
Caliper, facefilm + adhesive (micron)	ISO 534	200	
Gloss (GU)	ISO 2813, 60°	35	
Dimensional stability (mm max.)	FINAT FTM 14	0.15	
Shelf life (months)	Stored at 22° C/50-55 % RH	15	
Adhesive			
Tensile strength (N/mm ²)	ISO 527	>18	
Elongation (%)	ISO 527	>250	
Adhesion, initial 180° 20 min (N/m)	FINAT FTM-1, stainless steel	640	
Adhesion, ultimate 180° 72 hours (N/m)	FINAT FTM-1, stainless steel	800	
Temperature range			
Application temperature (Minimum: °C)		10	
Service temperature (°C to +°C)		-40 to 100	
Chemical properties²			
	Visual Inspection after exposure to following test fluids		
Gasoline	30 min	No significant change	
Car Wash solution	24 h	No significant change	
Diesel	24 h	No significant change	
Heptane	30 min	No significant change	
10% Sulfuric Acid	24 h	No significant change	
Motor oil	24 h	No significant change	
Solvent resistance	30 min	No effect exposed to: Isopropyl Alcohol	
Durability³			
	Zone 1	Zone 2	Zone 3
Vertical	10	8	6
Horizontal	7	4	3
Other tests			
Heat aging	500 h@90 °C	No significant change	
Water immersion	400 h@40 °C	No significant change	

Important

Information on physical and chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.

All technical data are subject to change. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.

1) Test methods: More information about our test methods can be found on our website.

2) Prolonged immersion in gasoline and similar fluids is not recommended.

3) Durability means that the products, subject to the limitations herein and Avery Dennison Product Data Sheets and Bulletins, and applied to recommended surfaces, shall not deteriorate excessively such as excessive film discoloration, excessive yellowing (dE>3, following the norm: PV3929), cracking, crazing, blistering, excessive gloss changes (gloss change >20%, following the norm PV3929), or excessive dimensional change or loss of adhesion, due solely to not meeting Seller's Specifications. Written instructions and detailed descriptions of the conditions under which the Avery Dennison products are assumed to be used and maintained can be found in the relevant Data Sheets and bulletins as found on.

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.

© 2026 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.