

## Solar Safety Window Film NT PerLite Ceramic 35i - 6 Mil- Neutral Interior Films



Low reflectance, high performance

**NT PerLite Ceramic 35i - 6 Mil** solar safety interior film is neutral grey in color and has excellent solar energy rejection that delivers comfort by cutting heat gain and glare. In addition, the reduced heat build up saves on cooling costs while the film's safety and security characteristics provide protection from shattered glass.

| Optical and Solar Properties**      | NT PerLite Ceramic 35 - 6 Mil |        |
|-------------------------------------|-------------------------------|--------|
| Item Number                         | R170L5T PS                    |        |
| Pane                                | Single                        | Double |
| Visible Light Transmitted           | 40%                           | 36%    |
| Visible Light Reflected (Interior)  | 16%                           | 18%    |
| Visible Light Reflected (Exterior)  | 18%                           | 24%    |
| Ultra Violet Block                  | 99%                           | 99%    |
| Total Solar Energy Reflected        | 19%                           | 22%    |
| Total Solar Energy Transmitted      | 29%                           | 25%    |
| Total Solar Energy Absorbed         | 52%                           | 53%    |
| Emissivity (Room Side)              | 0.90                          | 0.90   |
| Glare Reduction                     | 56%                           | 55%    |
| Selective InfraRed Reduction (SIRR) | 86%                           | 86%    |
| InfraRed Energy Rejection (IRER)    | 69%                           | 69%    |
| Shading Coefficient                 | 0.52                          | 0.63   |
| Solar Heat Gain Coeff. (G-Value)    | 0.44                          | 0.54   |
| U-Value Winter (IP)                 | 1.07                          | 0.49   |
| U-Value Winter (SI)                 | 6.08                          | 2.78   |
| Luminous Efficacy                   | 0.77                          | 0.58   |
| Total Solar Energy Rejected (%)     | 56%                           | 46%    |

<sup>\*\*</sup> Performance results are calculated on 3 mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.



S93004 4/19

| Mechanical Properties     |              |  |
|---------------------------|--------------|--|
| Thickness                 | 6 mil        |  |
| Tensile Strength at Break | 28,500 PSI   |  |
| Break Strength            | 145 lb/ inch |  |
| Elongation at Break       | 125%         |  |
| Peel Strength             | 7 lb/ inch   |  |
| Safety Testing            |              |  |
| Impact                    |              |  |
| AS/NZS 2208               | V            |  |

<sup>\*\*</sup> Performance results are calculated on 3 mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.



S93004 4/19