



Get Ready for the Sun

Avery Dennison® Automotive Window Films

NR Pro Series Non-Reflective Film

EXCELLENT SOLAR PERFORMANCE FOR COOL COMFORT

A cool and comfortable ride is what every driver experiences with Avery Dennison **NR Pro** automotive window films.

FEATURES AND BENEFITS

- > Exceptional aesthetics, no-fade warm graphite color
- > Broad range of light transmission levels
- > Premium heat rejection and up to 94% glare reduction, with minimal reflective effect
- > Blocks 99+% of harmful UV for ultimate driver comfort
- > Darker tints provide privacy for passengers and contents, for added peace of mind
- > Easy to install with excellent dot matrix fitting and optimal shrink capabilities
- > Stylish car upgrade without any signal interference (metal free)
- > Utilizes nanotechnology with a fusion of nano particles, to ensure high performance, durability and long-lasting color

Series	NR Pro Non-Reflective
Technology	Nanotechnology UV Stable Dye
Color Tone	Graphite
Construction	2-Ply Weatherable
Thickness	1.5 Mil
Warranty	Lifetime, Limited Non-Transferable ¹
Color Stable	Yes

EXPLORE THE LARGER PORTFOLIO

As part of its commitment to the auto restyling market, Avery Dennison is committed to a full portfolio of window films with a full range of aesthetic, performance and pricing options.

¹ For information on warranty terms, exclusions and certain limitations that apply please see the applicable product data sheets and other literature and bulletins on our website: graphics.averydennison.com




OPTICAL AND SOLAR PROPERTIES²

Film	Ultraviolet Block	Visible Light		Glare Reduction	SIRR ³	IRER ⁴	Shading Coefficient	Total Solar Energy				
		Transmitted	Reflected (Exterior)					Reflected	Transmitted	Absorbed	Rejected	
Non-Reflective												
NR Pro 05	R058P0A	>99%	6%	7%	94%	60%	43%	0.50	7%	25%	68%	57%
NR Pro 15	R058P9A	>99%	16%	7%	82%	49%	37%	0.59	6%	34%	60%	49%
NR Pro 20	R058P6A	>99%	22%	7%	76%	50%	37%	0.60	7%	37%	56%	48%
NR Pro 30	R058P8A	>99%	32%	7%	65%	45%	34%	0.66	7%	44%	49%	43%
NR Pro 35	R058P5A	>99%	37%	8%	58%	46%	34%	0.68	7%	45%	48%	41%
NR Pro 40	R058P4A	>99%	42%	8%	51%	43%	32%	0.71	8%	49%	43%	39%
NR Pro 50	R058P7A	>99%	52%	8%	39%	39%	29%	0.74	8%	55%	37%	36%

COOL GRAPHITE APPEARANCE⁵

The cool, non-fading graphite tone of **NR Pro** automotive window films are offered in seven VLT levels.



This image has been simulated and is not actual product comparison.

EASE OF INSTALLATION

Avery Dennison **NR Pro** automotive window films are designed for installation with outstanding heat-forming properties that tack fast, for a durable and secure fit. In addition, the PS adhesive is designed for an easy clean removal for effortless adjustments.

For information please contact: [windowfilm.orders@averydennison.com](mailto>windowfilm.orders@averydennison.com) or 1-800-660-5559

Avery Dennison

When selecting an Avery Dennison window film, know you are working with a global team of service obsessed, relentlessly curious inventors, engineers, and makers of pressure-sensitive materials, adhesives and coatings that stick on products you live with and dream about every day. We have a pioneering tradition of science-based innovation and corporate citizenship. Our special focus on automotive films, Supreme Wrapping™ Film vehicle wraps, and aftermarket effects places us in a unique position to help complete the total custom look of a vehicle.

For more about Avery Dennison, visit graphics.averydennison.com



Join the Avery Dennison
Graphics Solutions Community

²Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards.

³SIRR - Selective InfraRed Rejection: the percentage of IR radiation that is not directly transmitted through a glazing system. Calculated as %SIRR = 100% - % Transmission (@ 780-2500nm).

⁴IRER - InfraRed Energy Rejection: the percentage of Near Infrared Energy Rejection as measured between 780-2500nm. Calculated as the TSER over 780-2500nm: %IRER = 100% - 100*SHGC (@ 780-2500nm).

⁵Colors and tinting level are an approximate match. For a true color reference, please refer to the actual film sample.

All statements, technical information and recommendations about Avery Dennison products are based upon tests and information believed to be reliable but do not constitute a guarantee or warranty of any kind. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its intended and other purposes.



Graphics
Solutions

Avery Dennison Graphics Solutions

8080 Norton Parkway

Mentor, Ohio 44060

T: 1-800-660-5559

[windowfilm.orders@averydennison.com](mailto>windowfilm.orders@averydennison.com)